# **PVC PRESSURE SYSTEM**

### **PVC-M**



#### **PDHR09450**

#### DN450 x 6m PN9 Blue Rhino Series 2 PVC-M Pipe Reiber RRJ


**APPLICATION** Used for above or below ground applications to convey potable water in pressure applications.

#### **FEATURES**

- Australian Made
- BEP PVC Manufactured from Best Environmental Practice PVC
- Installation Economics
- Operation Efficiencies
- · Corrosion Resistant
- · Light weight
- Electrically non conductive

# TECHNICAL DATA PRODUCT PROPERTIES

Primary Material	PVC-M
Colour	Blue
Joint Type	RRJ
Rubber Ring Material	EPDM
Allowable Operation Temperature - Degrees	50°C
Allowable Operating Pressure - 20°C	900kPa
Average # of Joints per Litre – Iplex Lubricant	5
Unprotected UV Exposure (years)	2 Years
Maximum Diametric Deflection - 50 Years	7.50%
Minimum Radius of Curvature	135m
Socket Deflection	1°



#### **PRODUCT DIMENSIONS**

Category	Length	
Rating	PN9	
Length	6m	
Nominal	450mm	
ID	480.1mm	
Wall Thickness	13.5mm	
Socket Depth	289.2mm	

Max Socket Nominal OD	507mm	
Chamfer Detail	36mm	
Witness Mark	309mm	
Weight	195kg	
Crate Qty	2	
Crate Weight	390kg	

#### **ENVIRONMENTAL CREDENTIALS AND STANDARDS**

Environmental Accreditation	Best Environmental PVC - PVC Certificate No. BEP-PVC 0037	
Product Standard	AS/NZS 4765 "Modified PVC (PVC-M) Pipes for Pressure Applications"	
Standards Mark Certification SMK02730.4, SMK02468.4, SMK02748	WSAA Appraisal - PA1612	

## **MATERIAL PROPERTIES**

#### **MECHANICAL**

Density Specific Gravity	1.47
Ultimate Tensile Strength	38MPa
Yield Strain	5.5%
Compressive Strength	48MPa
Tensile Modulus	3000MPa
Hardness Shore D	85
Poissons Ratio	0.38
Design Stress	17.5MPa
Ring Bending Modulus (3mins)	3000MPa
Ring Bending Modulus (50Yrs)	1200MPa

#### **THERMAL**

Coefficient of Thermal Expansion	7x10 <sup>-5</sup> /°C
Thermal Conductivity	0.138W/m.K
Specific Heat	1047 J/kg/°C
Vicat Softening Temperature	>79°C
Flammability	Will not support combustion
Fire Index – Ignitability	2
Fire Index – Smoke Development	8
Fire Index – Spread of Flame	0
Fire Index – Heat Evolved	2

© Copyright: Iplex Pty Ltd 2019 all rights reserved. All drawings and information contained thereon are the exclusive property of Iplex Pipelines. Unless specifically noted, this drawing and information enclosed are subject to change at any time. Measures are for reference purpose only. If critical please contact Iplex Pipelines.



