PVC PRESSURE SYSTEM

PVC-0



PDRA16225

DN225 x 6m PN16 Apollo Blue Series 2 PVC-O Pipe Rieber RRJ

APPLICATION Used for above or below ground applications to convey potable water in pressure applications

FEATURES


- Australian Made
- BEP PVC Manufacutred from Best Environmental Practice PVC
- Installation Economics
- Operation Efficiences
- Corrosion Resistant

TECHNICAL DATA

PRODUCT PROPERTIES

Primary Material	PVC-O
Colour	Blue
Joint Type	RRJ
Rubber Ring Material	EPDM
Allowable Operation Temperature - Degrees	50°C
Allowable Operating Pressure - 20°C	1600kPa
Average # of Joints per Litre – Iplex Lubricant	14
Unprotected UV Exposure (years)	2 Years
Maximum Diametric Deflection - 50 Years	7.50%
Minimum Radius of Curvature	68m
Socket Deflection	1°

- · Light weight
- · Excellent Toughness and Ductility
- Large Internal Diameter and Smooth bore



PRODUCT DIMENSIONS

Category	Length
Rating	PN16
Length	6m
Nominal	225mm
ID	244.7mm
Wall Thickness	7.1mm

Socket Depth	202mm
Max Socket Nominal OD	306.2mm
Weight	53kg
Crate Qty	8
Crate Weight	424kg

ENVIRONMENTAL CREDENTIALS AND STANDARDS

Environmental Accreditation	Best Environmental PV	Best Environmental PVC - PVC Certificate No. BEP-PVC 0037	
Product Standard	AS/NZS 441 "Orientated PVC (PVC-O) Pipes for Pressure Applications"		
Standards Ma	ark Certification SMKP20188	WSAA Appraisal - PA1612	

MATERIAL PROPERTIES

MECHANICAL

Density Specific Gravity	1.47
Ultimate Tensile Strength	52MPa
Yield Strain	5.5%
Compressive Strength	66MPa
Tensile Modulus	4000MPa
Hardness Shore D	85
Poissons Ratio	0.38
Design Stress	28MPa
Ring Bending Modulus (3mins)	4000MPa
Ring Bending Modulus (50Yrs)	1800MPa

THERMAL

Coefficient of Thermal Expansion	7x10 ⁻⁵ /°C
Thermal Conductivity	0.138W/m.K
Specific Heat	1047 J/kg/°C
Vicat Softening Temperature	>79°C
Flammability	Will not support combustion
Fire Index – Ignitability	2
Fire Index – Smoke Development	8
Fire Index – Spread of Flame	0
Fire Index – Heat Evolved	2

©Copyright: Iplex Pty Ltd 2019 all rights reserved. All drawings and information contained thereon are the exclusive property of Iplex Pipelines. Unless specifically noted, this drawing and information enclosed are subject to change at any time. Measures are for reference purpose only. If critical please contact Iplex Pipelines.



