PVC PRESSURE SYSTEM

PVC-M



PDHR12225

DN225 x 6m PN12.5 Blue Rhino Series 2 PVC-M Pipe Rieber RRJ

APPLICATION Used for above or below ground applications to convey potable water in pressure applications.

FEATURES

- · Australian Made
- BEP PVC Manufactured from Best Environmental Practice PVC
- Installation Economics
- Operation Efficiencies
- · Corrosion Resistant
- · Light weight
- Electrically non conductive

195 6000 206

TECHNICAL DATA

PRODUCT PROPERTIES

Primary Material	PVC-M
Colour	Blue
Joint Type	RRJ
Rubber Ring Material	EPDM
Allowable Operation Temperature - Degrees	50°C
Allowable Operating Pressure - 20°C	1200KPa
Average # of Joints per Litre – Iplex Lubricant	14
Unprotected UV Exposure (years)	2 Years
Maximum Diametric Deflection - 50 Years	7.50%
Minimum Radius of Curvature	68m
Socket Deflection	1°

PRODUCT DIMENSIONS

Category	Length
Rating	PN12.5
Length	6m
Nominal	225mm
ID	241mm
Wall Thickness	9.2mm
Socket Depth	194.7mm

Max Socket Nominal OD	259.3mm
Chamfer Detail	25mm
Witness Mark	211mm
Weight	64kg
Crate Qty	8
Crate Weight	512kg

ENVIRONMENTAL CREDENTIALS AND STANDARDS

Environmental Accreditation	Best Environmental PVC - PVC Certificate No. BEP-PVC 0037	
Product Standard	AS/NZS 4765 "Modified PVC (PVC-M) Pipes for Pressure Applications"	
Standards Mark Certification SMK02730.4, SMK02468.4, SMK02748	WSAA Appraisal - PA1612	

MATERIAL PROPERTIES

MECHANICAL

Density Specific Gravity	1.47
Ultimate Tensile Strength	38MPa
Yield Strain	5.5%
Compressive Strength	48MPa
Tensile Modulus	3000MPa
Hardness Shore D	85
Poissons Ratio	0.38
Design Stress	17.5MPa
Ring Bending Modulus (3mins)	3000MPa
Ring Bending Modulus (50Yrs)	1200MPa

THERMAL

Coefficient of Thermal Expansion	7x10 ⁻⁵ /°C
Thermal Conductivity	0.138W/m.K
Specific Heat	1047 J/kg/°C
Vicat Softening Temperature	>79°C
Flammability	Will not support combustion
Fire Index – Ignitability	2
Fire Index – Smoke Development	8
Fire Index – Spread of Flame	0
Fire Index – Heat Evolved	2

©Copyright: Iplex Pty Ltd 2019 all rights reserved. All drawings and information contained thereon are the exclusive property of Iplex Pipelines. Unless specifically noted, this drawing and information enclosed are subject to change at any time. Measures are for reference purpose only. If critical please contact Iplex Pipelines.



