## **PVC PRESSURE SYSTEM**

### **PVC-M**



## PDHR16450 DN450 x 6m PN16 Blue Rhino Series 2 PVC-M Pipe Rieber RRJ


**APPLICATION** Used for above or below ground applications to convey potable water in pressure applications.

#### **FEATURES**

- Australian Made
- BEP PVC Manufactured from Best Environmental Practice PVC
- Installation Economics
- Operation Efficiencies
- Corrosion Resistant
- · Light weight
- · Electrically non conductive

# TECHNICAL DATA





#### PRODUCT DIMENSIONS

Category	Length	
Rating	PN16	
Length	6m	
Nominal	450mm	
ID	460.2mm	
Wall Thickness	23.4mm	
Socket Depth	289.2mm	

#### **ENVIRONMENTAL CREDENTIALS AND STANDARDS**

Environmental Accreditation	Best Environmental PVC - PVC Certificate No. BEP-PVC 0037
Product Standard	AS/NZS 4765 "Modified PVC (PVC-M) Pipes for Pressure Applications"
Standards Mark Certification SMK02730.4, SMK02468.4, SMK02748	WSAA Appraisal - PA1612

## **MATERIAL PROPERTIES**

#### **MECHANICAL**

Density Specific Gravity	1.47
Ultimate Tensile Strength	38MPa
Yield Strain	5.5%
Compressive Strength	48MPa
Tensile Modulus	3000MPa
Hardness Shore D	85
Poissons Ratio	0.38
Design Stress	17.5MPa
Ring Bending Modulus (3mins)	3000MPa
Ring Bending Modulus (50Yrs)	1200MPa

#### **THERMAL**

Coefficient of Thermal Expansion	7x10 <sup>-5</sup> /°C
Thermal Conductivity	0.138W/m.K
Specific Heat	1047 J/kg/°C
Vicat Softening Temperature	>79°C
Flammability	Will not support combustion
Fire Index – Ignitability	2
Fire Index – Smoke Development	8
Fire Index – Spread of Flame	0
Fire Index – Heat Evolved	2

© Copyright: Iplex Pty Ltd 2019 all rights reserved. All drawings and information contained thereon are the exclusive property of Iplex Pipelines. Unless specifically noted, this drawing and information enclosed are subject to change at any time. Measures are for reference purpose only. If critical please contact Iplex Pipelines.



