



**DR0215088HD**

**DN150 X 88D HD SN8 DWV PVC-U Bend FF x2 RRJ**

**APPLICATION** Changes direction of a pipeline conveying non-pressure sewage and greywater by 88°


### FEATURES

- BEP PVC - Manufactured from Best Environmental Practice PVC
- Installation Economics
- Operation Efficiencies
- Corrosion Resistant
- Tree root intrusion resistance
- Leakage Elimination

### TECHNICAL DATA

#### PRODUCT PROPERTIES

Primary Material	PVC-U
Colour	Grey
Joint Type	RRJ
Allowable Operation Temperature - Degrees	60°C
Allowable Operating Pressure - 20°C	900kPa
Average # of Joints per Litre – Iplex Lubricant	25
Unprotected UV Exposure (years)	2 Years



#### PRODUCT DIMENSIONS

Category	Bend/Elbow	Degree	88
Rating	SN8	Weight	2.26kg
Nominal	150mm	Carton Qty	6

### ENVIRONMENTAL CREDENTIALS AND STANDARDS

Environmental Accreditation	Best Environmental PVC - PVC Certificate No. BEP-PVC 0037
Product Standard	AS/NZS 1260 "PVC-U pipes and fittings for drain, waste and vent applications"
Watermark Certification 23900	WSAA Appraisal - PA1404

### MATERIAL PROPERTIES

#### MECHANICAL

Density Specific Gravity	1.47
Ultimate Tensile Strength	52MPa
Yield Strain	5.5%
Compressive Strength	66MPa
Tensile Modulus	2750MPa
Hardness Shore D	85
Poissons Ratio	0.38
Ring Bending Modulus (3mins)	3200MPa
Ring Bending Modulus (50Yrs)	1400MPa

#### THERMAL

Coefficient of Thermal Expansion	7x10 <sup>-5</sup> /°C
Thermal Conductivity	0.138W/m.K
Specific Heat	1047 J/kg/°C
Vicat Softening Temperature	75°C
Flammability	Will not support combustion
Fire Index – Ignitability	8
Fire Index – Smoke Development	8
Fire Index – Spread of Flame	0
Fire Index – Heat Evolved	1

©Copyright: Iplex Pty Ltd 2020 all rights reserved. Unless specifically noted, this drawing and information enclosed are subject to change at any time. Measures are for reference purpose only. If critical please contact Iplex Pipelines.

