PVC NON PRESSURE SYSTEM

STORMWATER



WPSO375 • DN375 x 6m SN2 Stormwater PVC-U Pipe SWJ

APPLICATION Used for above or below ground applications to convey rainwater or surface water.

FEATURES

- Australian Made
- BEP PVC Manufactured from Best Environmental Practice PVC
- Installation Economics

- · Operation Efficiencies
- · Corrosion Resistant
- Tree root intrusion resistance

TECHNICAL DATA PRODUCT PROPERTIES

Primary Material	PVC
Colour	White
Joint Type	SWJ
Allowable Operation Temperature - Degrees	50
Average # of Joints per Litre – Iplex Solvent	2
Average Number of Joints per Litre - Iplex Primer	6
Unprotected UV Exposure (years)	2 Years
Maximum Diametric Deflection -50yrs	7.5%

PRODUCT DIMENSIONS

Rating	SN2
Length	6m
UOM	LE
Nominal	400mm
ID	384.2mm
Wall Thickness	7.9mm
Weight	86.2kg
Crate Qty	6
Crate Weight	517.2kg



ENVIRONMENTAL CREDENTIALS AND STANDARDS

Environmental Accreditation Best Environmental PVC - PVC Certificate No. BEP-PVC 0037 | PVC Non Pressure Pipes EPD

Product Standard AS/NZS 1254 "PVC-U Pipes and Fittings for Stormwater and Surface Water Applications"

MATERIAL PROPERTIES

MECHANICAL

Density Specific Gravity	1.47
Ultimate Tensile Strength	52MPa
Yield Strain	5.5%
Compressive Strength	66MPa
Tensile Modulus	2750MPa
Hardness Shore D	85
Poissons Ratio	0.38
Ring Bending Modulus (3mins)	3200MPa
Ring Bending Modulus (50Yrs)	1400MPa

THERMAL

Coefficient of Thermal Expansion	7 x 10⁻⁵/°C
Thermal Conductivity	0.138W/m.K
Specific Heat	1047 J/kg/°C
Vicat Softening Temperature	75°C
Flammability	Will not support combustion
Fire Index – Ignitability	8
Fire Index – Smoke Development	8
Fire Index – Spread of Flame	0
Fire Index – Heat Evolved	1

© Copyright: Iplex Pty Ltd 2019 all rights reserved. All drawings and information contained thereon are the exclusive property of Iplex Pipelines. Unless specifically noted, this drawing and information enclosed are subject to change at any time. Measures are for reference purpose only. If critical please contact Iplex Pipelines.



