
## **PVC NON PRESSURE SYSTEM**

## **STORMWATER**



## W160751010 • DN75 x DN100 x DN100 Stormwater PVC-U Square Adaptor SWJ

**APPLICATION** Connects pipeline conveying rainwater or surface water to a square downpipe.

#### **FEATURES**


- Australian Made
- BEP PVC Manufactured from Best Environmental Practice PVC
- Installation Economics

- Operation Efficiencies
- Corrosion Resistant
- Tree root intrusion resistance

## TECHNICAL DATA PRODUCT PROPERTIES

| Primary Material                                  | PVC     |
|---|---------|
| Colour  | White   |
| Joint Type  | SWJ     |
| Allowable Operation Temperature - Degrees         | 50      |
| Average # of Joints per Litre – Iplex Solvent     | 60      |
| Average Number of Joints per Litre - Iplex Primer | 180     |
| Unprotected UV Exposure (years)                   | 2 Years |

#### **PRODUCT DIMENSIONS**



#### **ENVIRONMENTAL CREDENTIALS AND STANDARDS**

Environmental AccreditationBest Environmental PVC - PVC Certificate No. BEP-PVC 0037Product StandardAS/NZS 1254 "PVC-U Pipes and Fittings for Stormwater and Surface Water Applications"

# **MATERIAL PROPERTIES**

## MECHANICAL

| Density Specific Gravity     | 1.47    |
|------------------------------|---------|
| Ultimate Tensile Strength    | 52MPa   |
| Yield Strain                 | 5.5%    |
| Compressive Strength         | 66MPa   |
| Tensile Modulus              | 2750MPa |
| Hardness Shore D             | 85      |
| Poissons Ratio               | 0.38    |
| Ring Bending Modulus (3mins) | 3200MPa |
| Ring Bending Modulus (50Yrs) | 1400MPa |
|                              |         |

#### THERMAL

| Coefficient of Thermal Expansion | 7 x 10⁻⁵/ºC                 |
|----------------------------------|-----------------------------|
| Thermal Conductivity             | 0.138W/m.K                  |
| Specific Heat                    | 1047 J/kg/ºC                |
| Vicat Softening Temperature      | 75°C                        |
| Flammability                     | Will not support combustion |
| Fire Index – Ignitability        | 8                           |
| Fire Index – Smoke Development   | 8                           |
| Fire Index – Spread of Flame     | 0                           |
| Fire Index – Heat Evolved        | 1                           |

©Copyright: Iplex Pty Ltd 2019 all rights reserved. All drawings and information contained thereon are the exclusive property of Iplex Pipelines. Unless specifically noted, this drawing and information enclosed are subject to change at any time. Measures are for reference purpose only. If critical please contact Iplex Pipelines.





WWW.IPLEX.COM.AU • EMAIL INFO@IPLEXPIPELINES.COM.AU

PLUMBING, ELECTRICAL AND IRRIGATION 1300 0 IPLEX (1300 0 47539) • CIVIL 13 10 86