PVC NON PRESSURE SYSTEM

STORMWATER



W0249045 • DN90 x 45D Stormwater PVC-U Junction FF SWJ

APPLICATION To combine (or divide) rainwater or surface water flow and change direction of a pipeline.

FEATURES

- Australian Made
- BEP PVC Manufactured from Best Environmental Practice PVC
- Installation Economics


Operation Efficiencies


- Corrosion Resistant
- Tree root intrusion resistance

TECHNICAL DATA PRODUCT PROPERTIES

Primary Material	PVC
Colour	White
Joint Type	SWJ
Allowable Operation Temperature - Degrees	50
Average # of Joints per Litre – Iplex Solvent	60
Average Number of Joints per Litre - Iplex Primer	180
Unprotected UV Exposure (years)	2 Years

PRODUCT DIMENSIONS





ENVIRONMENTAL CREDENTIALS AND STANDARDS

Environmental Accreditation

Product Standard

Best Environmental PVC - PVC Certificate No. BEP-PVC 0037

AS/NZS 1254 "PVC-U Pipes and Fittings for Stormwater and Surface Water Applications"

MATERIAL PROPERTIES MECHANICAL

Density Specific Gravity	1.47	Co
Ultimate Tensile Strength	52MPa	
Yield Strain	5.5%	
Compressive Strength	66MPa	````
Tensile Modulus	2750MPa	
Hardness Shore D	85	
Poissons Ratio	0.38	Fir
Ring Bending Modulus (3mins)	3200MPa	F
Ring Bending Modulus (50Yrs)	1400MPa	

THERMAL

Coefficient of Thermal Expansion	7 x 10⁻⁵/ºC
Thermal Conductivity	0.138W/m.K
Specific Heat	1047 J/kg/ºC
Vicat Softening Temperature	75°C
Flammability	Will not support combustion
Fire Index – Ignitability	8
Fire Index – Smoke Development	8
Fire Index – Spread of Flame	0
Fire Index – Heat Evolved	1

©Copyright: Iplex Pty Ltd 2019 all rights reserved. All drawings and information contained thereon are the exclusive property of Iplex Pipelines. Unless specifically noted, this drawing and information enclosed are subject to change at any time. Measures are for reference purpose only. If critical please contact Iplex Pipelines.





WWW.IPLEX.COM.AU • EMAIL INFO@IPLEXPIPELINES.COM.AU

PLUMBING, ELECTRICAL AND IRRIGATION 1300 0 IPLEX (1300 0 47539) • CIVIL 13 10 86