# **PVC PRESSURE SYSTEM**

## **PVC-M**




#### PDHRL20100

## DN100 x 6m PN20 Purple Rhino Series 2 PVC-M Pipe Rieber RRJ

**APPLICATION** Used for above or below ground applications to convey recycled water in pressure applications.

#### **FEATURES**

- Australian Made
- BEP PVC Manufactured from Best Environmental Practice PVC
- Installation Economics
- Operation Efficiencies
- · Corrosion Resistant
- · Light weight
- Electrically non conductive



# **TECHNICAL DATA**

#### PRODUCT PROPERTIES

| Primary Material                                | PVC-M   |
|-------------------------------------------------|---------|
| Colour                                          | Purple  |
| Joint Type                                      | RRJ     |
| Rubber Ring Material                            | EPDM    |
| Allowable Operation Temperature - Degrees       | 50°C    |
| Allowable Operating Pressure - 20°C             | 2000kPa |
| Average # of Joints per Litre – Iplex Lubricant | 42      |
| Unprotected UV Exposure (years)                 | 2 Years |
| Maximum Diametric Deflection - 50 Years         | 7.50%   |
| Minimum Radius of Curvature                     | 30m     |
| Socket Deflection                               | 1°      |
|                                                 |         |

#### **PRODUCT DIMENSIONS**

| Category       | Length  |  |
|----------------|---------|--|
| Rating         | PN20    |  |
| Length         | 6m      |  |
| Nominal        | 100mm   |  |
| ID             | 107.8mm |  |
| Wall Thickness | 7.1mm   |  |
| Socket Depth   | 141.4mm |  |

| Max Socket<br>Nominal OD | 121.9mm  |
|--------------------------|----------|
| Chamfer Detail           | 17mm     |
| Witness Mark             | 154mm    |
| Weight                   | 22.40kg  |
| Crate Qty                | 36       |
| Crate Weight             | 805.80kg |

## **ENVIRONMENTAL CREDENTIALS AND STANDARDS**

| Environmental Accreditation                                   | Best Environmental PVC - PVC Certificate No. BEP-PVC 0037          |  |
|---------------------------------------------------------------|--------------------------------------------------------------------|--|
| Product Standard                                              | AS/NZS 4765 "Modified PVC (PVC-M) Pipes for Pressure Applications" |  |
| Standards Mark Certification SMK02730.4, SMK02468.4, SMK02748 | WSAA Appraisal - PA1612                                            |  |

## **MATERIAL PROPERTIES**

### **MECHANICAL**

| Density Specific Gravity     | 1.47    |
|------------------------------|---------|
| Ultimate Tensile Strength    | 38MPa   |
| Yield Strain                 | 5.5%    |
| Compressive Strength         | 48MPa   |
| Tensile Modulus              | 3000MPa |
| Hardness Shore D             | 85      |
| Poissons Ratio               | 0.38    |
| Design Stress                | 17.5MPa |
| Ring Bending Modulus (3mins) | 3000MPa |
| Ring Bending Modulus (50Yrs) | 1200MPa |

#### **THERMAL**

| Coefficient of Thermal Expansion | 7x10°5/°C                   |
|----------------------------------|-----------------------------|
| Thermal Conductivity             | 0.138W/m.K                  |
| Specific Heat                    | 1047 J/kg/°C                |
| Vicat Softening Temperature      | >79°C                       |
| Flammability                     | Will not support combustion |
| Fire Index – Ignitability        | 2                           |
| Fire Index – Smoke Development   | 8                           |
| Fire Index – Spread of Flame     | 0                           |
| Fire Index – Heat Evolved        | 2                           |

© Copyright: Iplex Pty Ltd 2019 all rights reserved. All drawings and information contained thereon are the exclusive property of Iplex Pipelines. Unless specifically noted, this drawing and information enclosed are subject to change at any time. Measures are for reference purpose only. If critical please contact Iplex Pipelines.



